

**PURPLE HYDRAULIC/PNEUMATIC SEALANT  
PART NO. 143473****PHYSICAL PROPERTIES****Monomer (Uncured)**

Base Compound .....	Methacrylate Ester
Appearance .....	Purple liquid
Viscosity .....	14,500 +/- 4,700 cps
Flash Point (TCC).....	300°F (149°C)
Gap Fill .....	.007"
Specific Gravity.....	1.1
Shelf Life @ 40°F .....	1 year unopened
RoHS-Compliant .....	Yes

**Polymer (Cured)**

Locking Strength .....	High
Service Temperature Range.....	-65°F to 300°F
Appearance.....	Purple solid
Full Cure Time .....	24 hours

**DESCRIPTION**

*Dynatex®* Purple Hydraulic/Pneumatic Sealant is a single-component anaerobic threadlocking adhesive designed for the locking and sealing of metal pipes and fittings. Seal hydraulic and pneumatic fittings up to 2" in diameter to resist high pressures and vibrational loosening. This product is specially formulated to offer high-lubricity for easy assembly and removal. Recommended for fine threaded fittings as used in hydraulic and pneumatic installations and small fittings. It contains no fillers or particles that could contaminate system fluids, foul valves or clog fine filters and screens. Excellent solvent resistance.

**FEATURES**

- Eliminates vibration issues
- Prevents rusting of threads
- Offers lubricity for easy assembly
- Can be adjusted or disassembled
- Seals against leakage

**TYPICAL APPLICATIONS**

- Small bolts in distributor
- Dash board assembly bolts
- Relay lock screws
- Idle control screws
- Small bolts in ignition systems
- Throttle body assembly bolts
- Set screw for rear view mirror

**CURING PERFORMANCE**

The gap of the bond line will affect set speed. Smaller gaps tend to increase the speed. Activators can be applied to improve set speed but may also impair overall adhesive performance.

**Packaging**

Colors: Purple  
Size: 50ml Bottle

## SOLVENT RESISTANCE

Sheer strength on steel after 500 hours.

Solvent	Resistance
Alcohol (Ethanol, Methanol)	+++
Ester (aromatic) (Ethylacetate)	- - -
Ketone (aromatic) (Acetone, Benzophenone)	- - -
Aliphatic Hydrocarbon (alkanes) (Petrol, Heptanes, Hexane)	++ -
Aromatic Hydrocarbons (Benzyl, (Toluol, Xylol)	++ -
Halogenated Hydrocarbons (Methylchloride, Chloroform, Chlorobenzol)	- - -
Weak aqueous (Nitrite, muriatic acid, sulphuric acid, phosphoric acid)	+++ (- - - if concentrated)
Weak aqueous base (sodium hydroxide solution, caustic potash)	+++ (- - - if concentrated)

## SETTING TIME (68°F, 65% R.H.)

Substrate	Set time/Full cure
Steel	30 min/24 hrs.
Brass	45 min/24 hrs.
Zinc-plated	60 min/24 hrs.
Stainless Steel	60 min/24 hrs.

## PERFORMANCE OF CURED MATERIALS

Bond strength after 24 hours at 20°C to 25°C on steel nuts and bolts

	Inch-pounds	Newton Meters
Breakaway Torque	20.0 to 60.0	2.26 to 6.78
Prevailing Torque	15.0 to 55.0	1.69 to 6.21

## GENERAL INSTRUCTIONS

Surfaces to be bonded should be clean and dry and free of grease.

Product should be applied in enough quantity to fill all engaged threads. The product performs best in thin bond gaps. Very large gaps may create gaps, which will affect the cure speed and overall strength. Good contact is essential. An adequate bond develops in 15 to 45 minutes and maximum strength is attained in 24 hours.

**This product is not recommended for use in pure oxygen environments and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.**

This product is not designed for plastics, particularly thermoplastics where stress cracking of the plastic could result. It is recommended to confirm compatibility of the product with all substrates prior to use.

## STORAGE AND SHELF LIFE

When stored in the original unopened containers at or below 90°F (32°C), *Dynatex® Purple Hydraulic/Pneumatic Sealant* has a shelf life of 12 months from date of shipment.

In Countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity. Cartons should always be stacked upright. DO NOT stack cartons on their side. **NEVER** stack cartons more than 8 high. DO NOT store within 1 meter (4 feet) of roofline of the warehouse or storage building.

## USERS PLEASE READ

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made. It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application. Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

**Non-warranty:** Because the storage, handling and application of the material is beyond Dynatex control, we can accept no liability for the results obtained. Dynatex sole limited warranty is the product meets the manufacturing specifications in effect at time of shipment. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. Dynatex will not be liable for incidental or consequential damages of any kind. The exclusive remedy for breach of such limited warranty is a refund of purchase price or replacement of any product shown to be other than as warranted.

Suggestions of uses should not be taken as inducements to infringe any patents.

**Dynatex®**  
a division of 

350 Ring Road  
Elizabethtown, KY 42701  
Email: sales@dynatex.net  
Toll Free: (800) 999-2937  
Ph: (270) 769-5557  
Fax (270) 769-6418  
Website: www.dynatex.net